

Hydrodrain FC6



Hydrodrain-FC6 is a geo-composite drainage layer comprising of a high performance single cusped HDPE (High Density Polyethylene) core with a geotextile filter thermally bonded to one side. The textile filter has a flap that extends beyond the core on one edge. The product is practically impermeable one side. It is used as an engineered drainage layer in structural applications, its major area of use being on roof decks and subsurface works.

Geotextiles

Type		Upper	
Material		Non-woven needle punched & heat treated long staple fibre.	
		Polypropylene	
Thickness at 2kPa	(mm)	1.2	EN ISO9863-1
Tensile strength (MD/CD)	(kN/m)	9.5 / 9.5	EN ISO 10319
Pore size O_{90}	(μ m)	120	EN ISO 12956
CBR puncture resistance	(N)	1 600	EN ISO 12236
Dynamic perforation cone drop	(mm)	32	EN ISO 13433

Drainage layer

Thickness at 2kPa	(mm)	6.1		EN ISO9863-1
Mass/unit area	(g/m^2)	0 670		EN ISO 9864
Tensile strength (MD/CMD)	(kN/m)	13 / 13		EN ISO 10319
Elongation (MD/CMD)	(%)	45 / 45		EN ISO 10319
CBR puncture resistance	(N)	2 250		EN ISO 12236
Water flow at 50mm head	($l/m^2.s$)	103		EN ISO 11058
At 2kPa permeability	(m/s)	2.5×10^{-3}		EN ISO 11058
Compressive Strength (unfilled)	(kPa)	250		
In plane water flow MD and CMD		HG=1.0	HG=0.1	
At 20kPa confining pressure	($l/m.s$)	1.60	0.48	EN ISO 12958
Life expectancy	(yrs)	120 years (manufacturers declaration)		
Resistance to chemicals		Excellent		EN 14030
Resistance to weathering		To be covered in 14 days		EN 12224

Product Dimensions

Standard roll dimension 1.1m x 50 m or 2.2 m x 25 m

Notes

- (1) The values given are indicative and correspond to nominal results obtained in our laboratories and testing institutes. The above figures have been obtained from statistical interpretation of test results. In line with our policy of continuous improvement the right is reserved to make changes without notice at any time.
- (2) The tolerance on roll length is 1.5% and on roll width is 1.0%
- (3) Final determination of the suitability of any information is the sole responsibility of the user. Blackdown will be pleased to discuss the use of this or any other product but responsibility for selection of material and its application in any specific project remains with the user.

Last updated Feb19

Blackdown Greenroofs

Address: Street Ash Nursery, Lisieux Way, Combe St Nicholas, Chard, St Nicholas, Chard, Somerset TA20 3HZ

Tel: 01460 234 582 Email: enquiries@blackdown.co.uk Web: www.blackdown.co.uk

A trading division of Alumasc Exterior Building Products Ltd - Company Registration No. 2992960 VAT Reg No. 395941796 UTR: 67545 65326